

0571



CRACK-STOPPER BLACKTOP ELASTOMERIC CRACK FILLER Data Sheet

- Lasts 2-3 Times Longer
- Fills Cracks Up to 3/4"
- Non-Shrink Formula

Crack Stopper® Rubberized Blacktop Crack Filler is formulated to provide a long lasting rubberized repair which expands and contracts with your driveway surface. Crack Filler has excellent flexibility and elongation in all temperatures. Won't track in summer temperatures. Fills cracks up to 1/2 - 3/4" wide.

PREPARATION: Free all cracks from any loose materials, dirt, or grease using a wire brush and Driveway Kleen™ Concentrated Driveway Cleaner. Rinse out area thoroughly with a high pressure hose and allow to dry.

APPLICATION: Make sure top is secured and shake thoroughly. Unscrew top and flip over spout. Cut tip on a 45° angle to desired opening (for smaller amounts cut closer to tip). Pour into crack filling slightly higher to allow for settling, but do not overfill. For larger holes and cracks use Crack Stopper® Drive Patch or RePave Permanent Pot Hole Patch. Allow 24 hours at good drying conditions (ie: above 65°F and under 50% relative humidity) prior to coating with a premium driveway sealer. Do not apply if rain is expected within 24 hours.

FOR BEST RESULTS: Apply when weather temperature is at least 65°F and rising.

CLEAN-UP: Clean tools with soap and water when wet, petroleum solvents or paint thinner when dried. Dried crack filler may be removed with a citrus based cleaner.

PRECAUTIONS: For exterior use only. Protective clothing and eyewear should be used during application of these products. When transporting this product, ensure that cap is tight and jug is secure and upright. Do not allow jug to tumble as this may cause cap to loosen and leakage to occur. Do not transport on passenger seats or inside the passenger compartment of any vehicle. Store product in the cargo area of vehicle, and secure over protective cloths to prevent damage due to accidental spills. Do not store at temperatures above 100°F. Do not allow to freeze. Do not reuse empty containers. Dispose of properly. Do not use in drinking water or food systems. KEEP FROM FREEZING.

COVERAGE RATE: 1 gallon will fill approximately 75 linear feet of 1/4" cracks.

TYPICAL PHYSICAL & PERFORMANCE CHARACTERISTICS

Weight Per Gallon, lbs.	9.6 lbs.
Residue by Evaporation, %	42 min.
Combustible Solvents	None
Consistency	Pourable
Cure Time (50% Relative Humidity, 70°F)	4-8 hours
Full Cure (50% Relative Humidity, 70°F)	24-48 hours
Application Temperatures	50°-120°F
Flammability	N/A
Clean-up Tools	Soap & water when wet mineral spirits when dry

Approx. Shipping Weights: (Note: All approx. weights include container.)
1 gallon (3.6 qt./3.4L) 9.6 lbs.

CAUTION!: HARMFUL OR FATAL IF SWALLOWED. KEEP OUT OF THE REACH OF CHILDREN.

Contains petroleum based products. Keep away from heat, sparks and open flame. Use only with adequate ventilation. Eye and skin irritant. In case of contact with eyes, flush with plenty of clean, room temperature water. Persons with skin or respiratory sensitivity should not use product without sufficient protection. Avoid contact with skin and breathing vapor. If swallowed, do not induce vomiting. Call physician immediately. Seal container when not in use.

CALIF. PROP. 65 • CHEMICAL WARNING: This product contains chemicals known to the State of California to cause cancer, birth defects or other reproductive harm. Use proper protection and adequate ventilation, when using product.

VOC/VOS: less than 10 g/L

ASPHALT C.A.S.# 8052-42-4
POLYMER C.A.S.# 9003-55-8
WATER C.A.S.# 7732-18-5
Product is asbestos free.
PATENT PENDING

Manufactured by/ fabricado por: Gardner-Gibson, Inc.,
P.O. Box 5449, Tampa, FL 33675
©2006 Gardner-Gibson, Inc.

WARRANTY AND DISCLAIMER:

For limited warranty and disclaimer information, contact the Gardner Asphalt corporate office at 1-800-237-1155.

See MSDS for more info



Gardner-Gibson, Inc. • P.O. Box 5449 • Tampa, Florida 33675-5449
Phone: (813) 248-2101 • Fax (813) 248-6768 • www.gardner-gibson.com